


Technical data


Duropal HPL ESA

Electrostatically dissipative high pressure laminate in postforming quality in accordance with EN 438-3:HGP/VGP, with robust melamine resin surface and sanded reverse.

Applications



Properties



Certificates



Melamine impregnated decorative paper

ESA impregnated craft paper, reverse side sanded

Specification			Unit	Test standard
	0.6	0.8		
Nominal thickness			mm	
Tolerance on thickness	± 0.1		mm	EN 438-2
Tolerance on length	+ 10		mm	EN 438-2
Tolerance on width	+ 10		mm	EN 438-2
Surface defects	max. 1 ¹⁾ max. 10 ²⁾		mm ² /m ² mm/m ²	EN 438-2
Edge defects	max. 20		mm	EN 438-2
Straightness of edges	max. 1.5		mm/m	EN 438-2
Squareness	max. 1.5		mm/m	EN 438-2
Flatness (length)	max. 60		mm/m	EN 438-2
Density	min. 1,350		kg/m ³	EN ISO 1183-1
Dimensional stability at elevated temperature (length)	max. 0.55		%	EN 438-2
Dimensional stability at elevated temperature (width)	max. 1.05		%	EN 438-2
Resistance to wet heat, 100 °C (other finishes)	min. 4		rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes)	min. 4		rating	EN 438-2
Resistance to surface wear	min. 150		cycles	EN 438-2
Resistance to scratching (textured finishes)	min. 3		rating	EN 438-2
Resistance to impact (small diameter ball)	min. 20		N	EN 438-2
Stain resistance (groups 1 & 2)	min. 5		rating	EN 438-2
Stain resistance (group 3)	min. 4		rating	EN 438-2
Resistance to colour change (xenon arc light)	4 to 5 Grey Scale Grade			EN 438-2
Reaction to fire	normally flammable			
Reaction to fire (Euroclass)	Euroclass D-s2,d0 or worse in connection with normally and easily flammable core boards.			EN 13501-1, CWFT acc. to 2003/593/EG

Technical data

Duropal HPL ESA

Specification			Unit	Test standard
Nominal thickness	0.6	0.8	mm	
Volume resistance R_D	$1 \times 10^4 - 1 \times 10^9 \text{ Ohm}^3$			EN 61340-5-1
Formaldehyde emission class	E1			EN 717-1
Formability (length)	min. $10 \times t^4$			EN 438-2
Formability (width)	Not determined, processing tests are to be carried out.			

¹⁾ Dirt, spots and similar surface defects

²⁾ Fibres, hairs and scratches

³⁾ measured dry, measurement voltage 100 V DC, cylindrical electrode, 20–30 °C and 20–50% rel. humidity (96 h conditioning)

⁴⁾ t = nominal thickness

Additional information

Product standard	<ul style="list-style-type: none"> in accordance with EN 438-3
Areas of application	<ul style="list-style-type: none"> Surface material for furniture and tabletops in ESD areas, e.g. at production and assembly workstations in the microelectronics industry. Also wherever electrostatic charges are to be prevented, such as on production lines, in laboratories or central control rooms.
Product safety	<ul style="list-style-type: none"> This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The decorative surface and the core consists of paper layers, which are impregnated with thermosetting resins. The resins harden completely during the manufacturing process by heat and high pressure. They form a stable, resistant and non-reactive material.
Special	<ul style="list-style-type: none"> Decors: W10140 Frontal White / U12188 Light Grey Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. The coarser the structure and the lighter the decor, the greater the scratch resistance. The smoother the structure and the darker the decor, the more sensitive it is to stains. Classification HGP / HGS / HGF is achieved with the surface textures recommended for horizontal applications. Requirements of classification VGP / VGS / VGF are met by all surface textures. Please refer to our sales documentation, to check which textures are available for this product.
Note	<ul style="list-style-type: none"> FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	<ul style="list-style-type: none"> Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Technical data

Duropal HPL ESA

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2022 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0
Fax +49 (0) 91 81 28 48 2
info@pfleiderer.com
www.pfleiderer.com